ESSENCE

MAHOGANY
CREAM
BROWN
GREY
WHITE



isla®

FASCINO ITALIANO

ESSENCE

5 COLOURS

mahogany
cream
brown
grey
white

3 SIZES

26,5x180 - 10 1/4”x72” Rett
20x120 - 8”x48” Rett
30x120 - 11 3/4”x48” Rett











ESSENCE
mahogany

20x120 - 8”x48” Rett

ESSENCE

mahogany

20x120 - 8”x48” Rett

ESSENCE

cream

20x120 - 8”x48” Rett



ESSENCE

cream

30x120 - 11 3/4”x48” Rett

ESSENCE
brown

30x120 - 11 3/4”x48” Rett

ESSENCE
brown

26,5x180 - 10 1/4”x72” Rett

ESSENCE

grey

20x120 - 8”x48” Rett

ESSENCE
white

Mosaico Esagona 20x30 - 10”x11 3/4”



ESSENCE
white

20x120 - 8”x48” Rett / Mosaico Intreccio 30x30 - 11 3/4” x11 3/4”

ESSENCE
mahogany

ESSENCE
cream

GRES PORCELLANATO SMALTATO
GLAZED PORCELAIN STONEWARE - GRES CERAME EMAILLE - GLASIERTES FEINSTEINZEUG - КЕРАМОГРАНИТ, ГЛАЗУРЬ НАНЕСЕНА ЦЫФРОВЫМ



1005039 26,5x180 - 10$^{1/4}$"x72" Rett

3 | 086



1004778 30x120 - 11$^{3/4}$"x48" Rett

4 | 068




1004777 20x120 - 8"x48" Rett

4 | 073



BATTISCOPA
1005035 9,8x120 - 3$^{7/8}$"x48" Rett

6 | 018



COSTA RETTA
1005036 30x120x3,3 - 11$^{3/4}$"x48"x1$^{5/16}$" Rett

2 | 94



26,5x180



1004652 26,5x180 - 10$^{1/4}$"x72" Rett

3 | 086



1004729 30x120 - 11$^{3/4}$"x48" Rett

4 | 068




1004644 20x120 - 8"x48" Rett

4 | 073



BATTISCOPA
1004666 9,8x120 - 3$^{7/8}$"x48" Rett

6 | 018



COSTA RETTA
1004733 30x120x3,3 - 11$^{3/4}$"x48"x1$^{5/16}$" Rett

2 | 94



26,5x180

ESSENCE
brown

ESSENCE
grey

GRES PORCELLANATO SMALTATO
GLAZED PORCELAIN STONEWARE - GRES CERAME EMAILLE - GLASIERTES FEINSTEINZEUG - КЕРАМОГРАНИТ, ГЛАЗУРЬ НАНЕСЕНА ЦЫФРОВЫМ



1004651 26,5x180 - 10$^{1/4}$"x72" Rett

3 | 086




1004728 30x120 - 11$^{3/4}$"x48" Rett

4 | 068




1004643 20x120 - 8"x48" Rett

4 | 073



BATTISCOPA
1004665 9,8x120 - 3$^{7/8}$"x48" Rett

6 | 018



COSTA RETTA
1004732 30x120x3,3 - 11$^{3/4}$"x48"x1$^{5/16}$" Rett

2 | 94

8,5 mm ▼ ▲ "3/8 | 10 mm ▼ ▲ "3/8 | V4

26,5x180



1004653 26,5x180 - 10$^{1/4}$"x72" Rett

3 | 086



1004730 30x120 - 11$^{3/4}$"x48" Rett

4 | 068




1004645 20x120 - 8"x48" Rett

4 | 073



BATTISCOPA
1004667 9,8x120 - 3$^{7/8}$"x48" Rett

6 | 018



COSTA RETTA
1004734 30x120x3,3 - 11$^{3/4}$"x48"x1$^{5/16}$" Rett

2 | 94

8,5 mm ▼ ▲ "3/8 | 10 mm ▼ ▲ "3/8 | V4

26,5x180

ESSENCE
white

GRES PORCELLANATO SMALTATO
GLAZED PORCELAIN STONEWARE - GRES CERAME EMAILLE - GLASIERTES FEINSTEINZEUG - КЕРАМОГРАНИТ, ГЛАЗУРЬ НАНЕСЕНА ЦЫФРОВЫМ



1004654 26,5x180 - 10$^{1/4}$"x72" Rett

3 | 086



1004731 30x120 - 11$^{3/4}$"x48" Rett

4 | 068




1004646 20x120 - 8"x48" Rett

4 | 073



BATTISCOPA
1004668 9,8x120 - 3$^{7/8}$"x48" Rett

6 | 018



COSTA RETTA
1004735 30x120x3,3 - 11$^{3/4}$"x48"x1$^{5/16}$" Rett


2 | 94

8,5 mm | 3/8"
10 mm | 3/8"
26,5x180

V4

ESSENCE
mosaici

essence mahogany



1005038 MOSAICO INTRECCIO
30x30 - 11$^{3/4}$"x11$^{3/4}$"


5 | 130



1005037 MOSAICO ESAGONA
25x30 - 10"x11$^{3/4}$"

5 | 230

essence cream



1004660 MOSAICO INTRECCIO
30x30 - 11$^{3/4}$"x11$^{3/4}$"


5 | 130



1004656 MOSAICO ESAGONA
25x30 - 10"x11$^{3/4}$"

5 | 230

essence brown



1004659 MOSAICO INTRECCIO
30x30 - 11$^{3/4}$"x11$^{3/4}$"

5 | 130



1004655 MOSAICO ESAGONA
25x30 - 10"x11$^{3/4}$"

5 | 230

essence grey



1004661 MOSAICO INTRECCIO
30x30 - 11$^{3/4}$"x11$^{3/4}$"

5 | 130



1004657 MOSAICO ESAGONA
25x30 - 10"x11$^{3/4}$"

5 | 230

essence white



1004662 MOSAICO INTRECCIO
30x30 - 11$^{3/4}$"x11$^{3/4}$"

5 | 130



1004658 MOSAICO ESAGONA
25x30 - 10"x11$^{3/4}$"

5 | 230

GRES PORCELLANATO SMALTATO

GLAZED PORCELAIN STONEWARE
GRES CERAME EMAILLE
GLASIERTES FEINSTEINZEUG
КЕРАМОГРАНИТ, ГЛАЗУРЬ НАНЕСЕНА ЦЫФРОВЫМ



26,5x180

Proprietà fisico chimiche/Physical-chemical properties Caracteristiques physiques-chimiques/physische Chemische eigenschaften	Norme/Norms Noemes Normen	Valori presvalori prescritti / Required values Valeurs exigees / Vorgeschriebene werte		
Dimensioni Sizes Format Format	ISO 10545-2	Lunghezza e larghezza Length and width Longueur et largeur Länge und Breite	(± 0,75% 190 cm² < 410 ≤) (± 0,6 % > 410 cm2)	± 0,3% max ± 1,5 mm
		Rettilineità spigoli Linearity Rectitude de l'angularité Kantengeradheit	(± 0,5% max)	± 0,3% max ± 1,5 mm
		Ortogonalità Wedging Orthogonalité Rechtwinkligkeit	(± 0,6% max)	± 0,3% max ± 1,5 mm
		Planarità Warpage Planéité Ebenflächigkeit	(± 5% max)	± 0,5% max ± 1,5 mm
	ASTM C485			Warpage diagonal/edge ± 0,4%
Spessore Thickness Épaisseur Stärke	ISO 10545-2		(± 5% max)	10 mm / 8,5 mm
Assorbimento d'acqua Water absorption Absorption d' eau Wasseraufnahme	ISO 10545-3		≤ 0,5% GRUPPO Bla GL	E ≤ 0,1% Bla GL
Resistenza a flessione e forza di rottura Moduls of rupture and breaking strength resistance à la flexion et force de rupture Biegfestigkeit und Bruchlast	ISO 10545-4		S ≥ 1300 N	S ≥ 1300 N
			R ≥ 35 N/mm²	R ≥ 35 N/mm² ²
Resistenza agli sbalzi termici Thermal shocks resistant Résistance aux variations thermiques Temperaturwechselbeständigkeit	ISO 10545-9		Requisito non previsto Not provided requirement Qualité pas previe Erfordernis nicht vorgesehen	Resistente Resistant Résistant Widerstandsfähigkeit
Resistenza al gelo Frost resistance Résistance au gel Frostständigkeit	ISO 10545-12		Nessuna alterazione No alteration Aucune altération Keine Änderung	Resistente Resistant Résistant Widerstandsfähigkeit
Resistenza alla abrasione della superficie di piastrelle smaltate Resistance to surface abrasion of glazed tiles Résistance à l'abrasion de la surface des carreaux émaillés Widerstand gegen Abrieb der Oberfläche der glasierten Fliesen	ISO 10545-7			Classe 4 Class 4 Classe 4 Gruppe 4
Coefficiente di dilatazione termica lineare (50°/400°) Linear thermal expansion coefficient (50°/400°) Dilatation thermique linéaire (50°/400°) Lineare Wärmeausdehnung (50°/400°)	ISO 10545-8			Metodo disponibile Test method available Méthode disponible Verfügbares Verfahren
Durezza della Superficie Surface resistance Dureté de la surface Ritzhärte deo Oberfläche	EN 101			> 6
Resistenza all'attacco chimico (tranne acido fluoridrico) Resistance to chemical attack (except hydrofluoric acid) Résistance à l'attaque chimique (sauf acide fluoridrique) Säure-und Laugenbeständigkeit (außer Flußsäure)	ISO 10545-13		Come indicato dal produttore As indicated by manufacturer Comme indiqué par le producteur Wie vom Hersteller angegeben	Classe A - LA - HA Class A - LA - HA Classe A - LA - HA Gruppe A - LA - HA
Resistenza alle macchie Resistance to staining Résistance aux taches Fleckbeständigkeit	ISO 10545-14		CLASSE min. 3	Classe 5 Class 5 Classe 5 Gruppe 5
Coefficiente di attrito Coefficient of friction Coefficient de frottement Reibungskoeffizient	DIN 51130			R10
Resistenza alla scivolosità. Coefficiente di attrito medio Skid resistance. Average coefficient of friction Résistance au glissement. Coéfficient de frottement moyen Rutschfestigkeit. Mittlerer Reibungswert	DIN 51097			Classe B Class B Classe B Gruppe B
	B.C.R.A. (No Lapp)		μ > 0,40 (Wet) μ > 0,40 (Dry)	0,40 ≤ 𝑀 ≤ 0,74
	DCOF Acu Test (No Lapp)		≥ 0,42	𝑀 ≥ 0,42
Variazione cromatica Colour shading Variations chromatiques Chromatische Abweichungen				V 4

IMBALLI - PACKING TABLE - TABLEAU DES EMBALLAGES - VERPACKUNGS TABELLE - УПАКОВКА

FORMATO SIZE	SCATOLA - BOX			PALLET		
	Pezzi - Pieces	m²	KG	Scatole - Boxes	m²	KG
26,5x180 - 10 1/4"x72" Rett	3	1,43	28,50	36	51,48	1.026,00
20x120 - 8"x48" Rett	4	0,96	21,30	36	34,56	786,00
30x120 - 11 3/4"x48" Rett	4	1,44	32,70	24	34,56	820,00
30x30 - 11 3/4"x11 3/4" Mosaico Intreccio	5	0,45	9,00	60	27,00	560,00
25x30 - 10"x11 3/4" Mosaico Esagona	5	0,38	8,00	60	22,50	500,00

CE

NGT SPA
VIA PLATONE 9
42048 RUBIERA (RE)

05
001NGT2013-07-01

EN 14411:2012

Piastrelle di ceramica pressate a secco, con assorbimento di acqua $E_b \leq 0,5\%$, per pavimentazioni interne ed esterne.

Dry pressed ceramic tile, with water absorption $E_b \leq 0,5\%$, for internal and external floorings.

Terza edizione: Settembre 2018
Coordinamento: Ufficio Marketing
Foto: Hipix
Fotoelaborazioni: Hipix
Stampa: Intese grafiche
© Copyright 2018 Gruppo Romani S.p.A.

09.2018.3000

isla®

FASCINO ITALIANO

SEDE COMMERCIALE E LOGISTICA
VIA PLATONE, 9 - 42048 RUBIERA (RE) - ITALY
TEL. +39 0522-622690 - FAX +39 0522 1602001
WWW.ISLATILES.IT - INFO@ISLATILES.IT

NGT SPA - SEDE LEGALE E AMMINISTRATIVA:
VIA A. VOLTA 9 - 42013 CASALGRANDE RE - ITALY
TEL +39 0522 998411 - FAX +39 0522 999515